



POLYESTER WHITE GLOSS TC 50 μ m-SUPERTACK- KRAFT 135gsm FLAT

Issue: 01/02/2018 Modification: 0 page 1/1

GENERAL PRODUCT CHARACTERISTICS

Total weight 225 gsm \pm 6% ISO 536 Total caliper 204 μ m \pm 8% ISO 534

FACE:

white gloss polyester film, top coated for excellent ink and toner adhesion on laser printers (B&W and colour) and copiers.

Substance 72 gsm \pm 3 Caliper 51 μ m \pm 3

ADHESIVE

Water emulsion acrylic based Supertack type, high initial tack and strong permanent bond for general use. Recommended on a wide variety of substrates, including paper, board, glass, steel

Peel adhesion 10.9 N/inch \pm 1 FINAT1 Shear test 20h \pm 5 FINAT8 Quick stick 7,6 N/inch \pm 1 FINAT9

 $\begin{array}{ll} \mbox{Min. application temp.} & +5^{\circ}\mbox{C} \\ \mbox{Service temp. Range} & -20^{\circ}\mbox{C}/+90^{\circ}\mbox{C} \end{array}$

BACKING

One-side coated white kraft, solventless silicon coated. High dimensional stability, especially suitable for self-adhesive films.

Substance 135 gsm \pm 8 ISO 536 Caliper 139 μ m \pm 9 ISO 534

SAFETY REGULATIONS

• The adhesive coating and backing paper meet the European Standard EN71-3:2013 "Safety of Toys" - Migration of certain elements

• THE FACE MATERIAL IS ROHS COMPLIANT

APPLICATIONS

Hi-quality labels and tags, high resolution labels for barcodes, variable information labelling. Suitable for outdoor application. Good dimensional stability and ageing resistance.

Trials are recommended, by the purchaser, prior to use, on the intended substrates for product suitability.

PRINTABILITY

Face: suitable for laser print and Led-toner (B&W and colour) subject to toners compatibility

Consult your inks supplier about suitable printing inks to obtain maximum ink bonding

Backing: good printing results by all common print processes, in one or more colours

ON REQUEST

Forest Stewardship Council certified backing material. Splits on the release paper, standard spacing 38mm or customized.

SHELF LIFE AND USE

Two (2) years from delivery date when stored at the following conditions:

- Temperature +5°C/+35°C.
- Relative Humidity 45% 60%.
- Store in a cool dry place.
- Store away from heaters or direct sunlight or rain.
- Keep the sheets flat, the reels piled.
- Store in the original packaging, remove packaging just before Use
- Material to be acclimatized at least 24 hrs to ambient conditions.

All ITALSTICK products are subject to careful quality control throughout the production process and are warranted to be free from manufacturing defect and of quality.

The reported information is based upon research and tests the Company believes to be reliable; such information does not constitute a warranty. The purchaser and/or user should carefully test, prior to use, suitability and performance of the product for the intended use and shall assume all risks for such use. ITALSTICK shall not be liable for damages beyond the replacement value of the defected product nor for incidental or consequential damages

All technical data are subject to change without prior notice.

This revision cancels and replaces the previous one.

ITALSTICK Soc. Coop. via della Stazione, 6 I-41019 Soliera www.italstick.com Ph. +39 059 566705 Fax +39 059 565127 info@italstick.com